

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 January 2001 (18.01.2001)

PCT

(10) International Publication Number
WO 01/04050 A1

(51) International Patent Classification?: **C01B 33/44**,
C08K 9/04, C08J 3/20

(NL). **RENTROP, Cornelis, Hermanus, Arnoldus**
[NL/NL]; Carré 141, NL-5017 JG Tilburg (NL).

(21) International Application Number: PCT/NL00/00479

(74) Agent: **PRINS, A. W.**: Vereenigde, Nieuwe Parklaan 97,
NL-2587 BN The Hague (NL).

(22) International Filing Date: 7 July 2000 (07.07.2000)

(25) Filing Language: Dutch

(26) Publication Language: English

(30) Priority Data:
1012587 13 July 1999 (13.07.1999) NL
1013373 22 October 1999 (22.10.1999) NL

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **NED-
ERLANDSE ORGANISATIE VOOR TOEGEPAST-
NATUURWETENSCHAPPELIJK ONDERZOEK
TNO** [NL/NL]; Schoemakerstraat 97, NL-2628 VK Delft
(NL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **FISCHER, Hart-
mut, Rudolf** [DE/NL]; Dalkruid 13, NL-5713 TP Mierlo
(NL). **BATENBURG, Lawrence, Fabian** [NL/NL];
Heikampen 93, NL-5672 SV Nuenen (NL). **MEINEMA,
Harmen, Anne** [NL/NL]; Landweg 287, NL-3833
VJ Leusden (NL). **HOGERHEIDE, Marinus, Pieter**
[NL/NL]; Meerten Verhoffstraat 73, NL-4811 AR Breda

Published:

- With international search report.
- Before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments.

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: **NANOCOMPOSITE COATINGS**

(57) Abstract: The invention relates to a method for preparing a composition for coating, wherein a layered, inorganic filler is subjected to an ion exchange with a modifier, which modifier comprises at least two ionic groups, which groups are separated from each other by at least four atoms, and wherein the modified filler, together with a polymer, is dispersed in a diluent.

WO 01/04050 A1

Title: Nanocomposite coatings

This invention relates to a composition for forming a coating, and to a coating formed from such composition.

In the literature, it has already been proposed several times to incorporate a layered inorganic filler, such as a clay, into a coating.

5 A difficulty here, however, is that compositions for coatings are normally based on polymeric systems in a diluent. These polymeric systems often have a hydrophobic character, whereas the filler has a more hydrophilic character. This makes the two components intrinsically immiscible.

10 There are different, more and less successful procedures known for alleviating the problem of the intrinsic immiscibility of the two materials. In most cases, to that end, an ion exchange is carried out, whereby ions between the sheets of the layered filler are exchanged for ions which have an organic character, which makes them compatible with the polymeric matrix.

15 Although in publications on this subject it is mentioned in most cases that the above-described method for uniting the layered filler and a polymeric matrix relates to both polymeric bulk materials and coatings, in practice only the issues involved in bulk materials are addressed.

20 In the case of coatings, there is, in addition to the above-outlined problem of the intrinsic immiscibility, another problem. After application, a composition for a coating should cure into a solid coating. This not only requires that the diluent evaporates, but also that a curing reaction occurs. This reaction is mostly initiated and/or catalyzed by heat, oxygen, addition of an extra reactant (crosslinking agent) or light (UV radiation). Of course,
25 the presence of the layered filler should not disturb the curing process. It has been found that this problem has not been adequately resolved yet in the prior art.

In European patent application 0 791 556 a water-dispersible organic clay complex is described, in which a quaternary ammonium ion is present in the interlamellar space of an expansible phyllosilicate. The ammonium ion comprises an oxypropylene unit and an oxyethylene unit.

5 The complex is used for controlling the rheology of a water-based coating agent.

The international patent application 98/56598 relates to a barrier coating consisting of an elastomer and a dispersed, layered filler in a liquid carrier. The coating is used in particular in (car) tires. In order to enable proper dispersion of the filler, which is preferably vermiculite, and the elastomer, in the liquid carrier, use is made of a surfactant. Examples of suitable surfactants that are mentioned are known wetting agents, antifoam agents, emulsifiers, dispersing agents and the like. Preferably, nonionic surfactants are used.

15 The object of the present invention is to provide a coating composition comprising a layered, functional inorganic filler, a polymeric matrix and a diluent, which does not have the disadvantages of the known compositions. What is contemplated in particular is that the composition, after being applied, cures to form a coating having very good properties, in particular barrier properties. It is then desirable that the filler has no or hardly any adverse effect on the curing reaction of the composition. What is further contemplated is for the filler to be homogeneously dispersed through the composition.

25 Surprisingly, it has presently been found that these objects can be achieved by subjecting the layered, inorganic filler to an ion exchange with a modifier before incorporating the filler in a composition for a coating, which modifier comprises at least two ionic groups, which groups are separated from each other by at least four atoms. Thus, the invention relates to a method for preparing a composition for a coating, wherein a layered, inorganic filler is subjected to an ion exchange with a modifier,

30

which modifier comprises at least two ionic groups, which groups are separated from each other by at least four atoms, and wherein the modified filler, together with a polymer, is dispersed in a diluent.

What is achieved according to the invention by the use of the specific modifier is that the layered inorganic filler together with the polymer is homogeneously dispersed in the diluent. Further, it has been found that the modified filler substantially does not have any adverse effect on the curing of the composition when it has been applied for forming a coating. The cured layer has particularly favorable properties, such as a reduced permeability to gases and liquids, and an improved heat resistance. Further, the coating has been found to possess improved surface properties (resistance to scratches and the like), without this affecting the bonding of the layer to a substrate or the flexibility of the layer.

The layered inorganic filler which is used according to the invention can be both cationic and anionic in nature. In principle, any anionic or cationic filler obtained synthetically or from a natural source can be used. Suitable examples can be selected from the classes of clays and layered double hydroxides.

Eminently suitable are clay types based on layered silicates, such as layered phyllosilicate which is made up of magnesium and/or aluminum silicate layers each about 7-12 Å thick. Particularly preferred are smectite-type clay minerals such as montmorillonite, saponite, hectorite, fluorohectorite, beidellite, nontronite, vermiculite, halloysite and stephanite. These materials impart very favorable mechanical properties and an increased thermal stability to a coating.


A suitable clay type preferably has a cation exchange capacity of 30 to 250 milliequivalents per 100 grams. When that capacity is higher than the upper limit mentioned, it proves to be difficult to finely disperse the clay at a molecular level because of the strong mutual interaction of the layers of clay. When the cation exchange capacity is lower than the lower limit

mentioned, the clay proves to be difficult to modify in that the interaction with the modifier is small. Preferably, a clay is used having a cation exchange capacity of from 50 to 200 milliequivalents per 100 grams.

Another layered, inorganic filler that can be used according to the invention is a layered double hydroxide (LDH). This material is a so-called anionic clay, consisting of small crystalline sheets of dimensions of a few nanometers, between which anions are located. By these anions are meant anions other than hydroxyl groups. A layered double hydroxide can be both natural and synthetic in nature. For a description of possible methods of preparation for a synthetic layered double hydroxide, reference is made to U.S. Patents 3,539,306 and 3,650,704.

Preferably, the layered double hydroxide has a large contact surface and an ion exchange capacity of 0.5 to 6 milliequivalents per gram. An LDH preferably used is a hydrotalcite or a hydrotalcite-like material, because these materials can be easily prepared synthetically, while the desired properties can be eminently controlled.

Found to be uncommonly suitable are hydrotalcites that satisfy the formula (I):



wherein M^{2+} is a bivalent cation, M^{3+} is a trivalent cation, x is a number between 0.15 and 0.5, y is 1 or 2, n is a number from 1 to 10, and A is an anion selected from the group consisting of Cl^- , Br^- , NO_3^- , SO_4^{2-} and CO_3^{2-} . The bivalent cation is preferably selected from the group of bivalent magnesium, zinc, nickel, iron, copper, cobalt, calcium and manganese ions and combinations of these bivalent cations. Most preferably, the bivalent cation is a magnesium, zinc or calcium ion or a combination thereof. The trivalent cation is preferably selected from the group of trivalent aluminum, chromium, iron, cobalt and manganese ions and combinations of these trivalent cations. Most preferably, the trivalent cation is an aluminum, chromium or iron ion or a combination thereof.

It is preferred that the filler, when it is being processed according to the invention, contains substantially no agglomerates of sheets which form the layered structure of the filler. Under normal circumstances the sheets form agglomerates, whereby they stack onto each other. According to the invention, it is preferred to substantially break these agglomerates, so that discrete sheets with a relative distance between the sheets of at least 50 Å, preferably at least 75 Å, and still more preferably at least 100 Å are formed. This distance can be suitably determined using x-ray diffraction techniques.

An example of a suitable procedure for breaking the agglomerates, i.e., for deagglomeration, is a method whereby the filler is dispersed in, preferably, water that is substantially free of ions. This water preferably has a temperature of 20-60°C. Preferably, the amount of filler is not more than 10% by weight, based on the dispersion, so that the viscosity remains low. This has a positive effect on the processability of the dispersion. Thereafter, the filler is allowed to swell for a period between half an hour and a few hours. Other methods of breaking the agglomerates in the filler are known to those skilled in the art.

According to the invention, the filler is subjected to an ion exchange with the modifier.

An important part of the invention is formed by the specific choice of the modifier. This is a compound which comprises at least two ionic groups, with at least four, preferably at least seven, atoms located between the two ionic groups. It has been found that a particularly homogeneous distribution of the modified filler in the composition is obtained when the modifier comprises an aromatic group, such as an optionally substituted benzene or naphthalene group. This advantage is noticeable especially when the aromatic group is located between the at least two ionic groups.

The nature of the ionic groups will depend on the kind of filler that has been selected. When the filler is a cationic clay, at least one ionic group

will be cationic. Good results have been achieved with ammonium, sulfonium and phosphonium groups. When the filler is a layered double hydroxide, at least one ionic group will be an anionic group. Examples of suitable anionic groups are carboxylate, sulfonate and phosphonate groups.

5 In a preferred embodiment, the modifier is a dye. In that way, the modifier can be utilized to give a coating a particular desired color. Suitable are cationic and anionic dyes and dyes which can be brought into cationic or anionic form by protonating or deprotonating. These are, for instance, dyes with N^+ , P^+ , S^+ functionalities and/or derivatives thereof. Additionally
10 preferred are dyes with anionic functionalities such as RCO_2^- , $RP(O)O_2^{2-}$ and RSO_3^- , wherein R is defined as an alkyl, aryl or alkylaryl group. Also preferred are dyes where the charge is divided over different functional groups. Examples of suitable dyes are mentioned inter alia in Ullmanns Encyklopädie der technische Chemie, band 11, Verlag Chemie, Weinheim,
15 1976 under "Farbstoffen".

The ion exchange can take place by adding a solution of the modifier to a dispersion of the filler in warm water, preferably the dispersion described above. The modifier is preferably dissolved in water in a concentration of between 1% and 50%. The amount of modifier that is
20 used in the ion exchange is selected depending on the ion exchange capacity (CEC) of the filler and molar mass and number of reactive and/or ionic groups of the modifier. The pH of the modifier solution is preferably between 2 and 10, depending on the selected filler and the modifier, and can be adjusted with suitable buffers. The amount of modifier used is preferably
25 50 to 150% of the ion exchange capacity of the filler (clay).

After the ion exchange, the modified filler is preferably washed a few times with water and filtrated. If desired, the material can be dried, for instance in an oven or by spray-drying or freeze-drying, whereafter it can be ground to form a powder to improve processability. The material thus

obtained can be formulated in a conventional manner in a composition for a coating.

To that end, in a random order, the modified filler and the polymer are dispersed in a suitable diluent. It has been found that especially
5 compositions based on polar diluents such as water, alcohols (ethanol), ethers, esters, ketones (acetone) and combinations thereof, benefit from the invention.

The polymer is mixed with the diluent and the modified filler, whereafter the whole composition is homogeneously mixed by means of
10 known dispersion techniques, such as mechanical stirring, ultrasound vibration, dispersing, etc. Depending on the nature of the curing reaction, initiator, additives and pigments can be added to the composition. The initiator content is normally about 0.01 to 10% by weight with respect to polymerizable units, preferably between 0.1 and 1% of the polymerizable
15 units. The additive content can range between 0 and 15% by weight of the whole composition, preferably between 0 and 3%. The pigment content can range between 0 and 50% by weight, being preferably between 0 and 25%. It is also possible to prepare a coating formulation completely, whereafter the modified filler is added. A homogeneous mixture is obtained according
20 to techniques known to those skilled in the art, such as ultrasonically vibrating the whole for, for instance, 30 minutes.

The polymer that is included in the composition can be any polymer that is conventional in compositions for coatings.

The following polymers can be used in the present composition:
25 polyurethanes; polyacrylates; polymethacrylates; polyesters; polyethers; polyolefins; polystyrene; polyvinyl chloride; alkyds; nitrocellulose; epoxides; phenol resins; amino resins; silicones; polysiloxanes, and organic-inorganic hybrid materials; and combinations thereof. The following polymers are preferred: polyurethanes; polyacrylates; polysiloxanes; polyesters;
30 polyethers and organic-inorganic hybrid materials. Organic-inorganic

hybrid materials are understood to be materials which are built up from a combination of polymeric organic and inorganic/ceramic components which are mutually chemically bonded on a molecular level, which may further contain inorganic nanoparticles dispersed therein.

5 The composition can be used for applying coatings in a conventional manner. Suitable application procedures are, for instance, pouring, misting, brush application and the like. After application, the diluent evaporates (drying) and a curing takes place. The present composition is suitable for applying coatings to substrates of all kinds.

10 Examples of materials on which the substrate may be based comprise wood, metal, plastic, glass, textile and the like.

 The invention will presently be further elucidated in and by the following examples.

15 Example 1

 20 Grams of an EXM 757 clay were dispersed in an excess of water and subjected to a reaction with 6.1 grams of methylene blue (95 meq methylene blue, based on 100 grams of solid clay, which is 100% of the exchange capacity of the clay). After stirring for 30 minutes at 60°C, the
20 solid clay, modified with methylene blue, was filtrated, and purified until there were no traces of chlorine ions present anymore. The material obtained was subsequently freeze-dried.

 The thus modified clay was used in a water-carried polyurethane/polycarbonate diol composition (NeoRez R986, commercially
25 available from Zeneca Resins B.V., solids content 35%). To that end, 1.02 grams of the modified clay were mixed with the composition, so that a product was obtained which contained 2.5% by weight of clay, based on the total amount of solid material. The mixture was stirred until no solid particles were visible anymore.

Of the composition that was thus obtained, coatings of a thickness of 90 μm were applied to substrates of steel, glass and aluminum. In addition, such a coating of the water-carried polyurethane/polycarbonate diol composition without modified clay was applied. Of all the coatings, no differences worth mentioning in pencil hardness (ASTM D3363-92A), bend test flexibility (ASTM D 522-93A) and cross-hatch adhesion (ASTM D 3359-95) could be demonstrated. The clay-containing layers proved to be 42% less permeable to moisture (ASTM E96).

Example 2

20 Grams of an EXM 757 clay were dispersed in an excess of water and subjected to a reaction with 5.1 grams of methylene red (95 meq methylene red, based on 100 grams of solid clay, which is 100% of the exchange capacity of the clay). After stirring for 30 minutes at 60°C, the solid clay, modified with methylene red, was filtrated, and purified until there were no traces of chlorine ions present anymore. The material obtained was subsequently freeze-dried.

The thus modified clay was used in a water-carried acryl/styrene composition (Neocryl XK-62, commercially available from Zeneca Resins B.V., solids content 42%). To that end, 0.67 grams of the modified clay were mixed with the composition, so that a product was obtained which contained 2.5% by weight of clay, based on the total amount of solid material. The mixture was stirred until no visible solid particles were visible anymore.

Of the composition that was thus obtained, coatings of a thickness of 90 μm were applied to substrates of steel, glass and aluminum. In addition, such a coating of the water-carried acryl/styrene composition without modified clay was applied. Of all the coatings, no differences worth mentioning in hardness, flexibility and adhesion could be demonstrated. By means of thermographic analysis techniques, it was established that the

clay-containing layers proved to have a 30°C higher degradation temperature.

Example 3

5 20 Grams of an EXM 757 clay were dispersed in an excess of water and subjected to a reaction with 4.2 grams of methylene blue sodiumaminoundecanate (95 meq 4-amino-1-naphthalenesulfonic acid, based on 100 grams of solid clay, which is 100% of the exchange capacity of the clay). After stirring for 30 minutes at 60°C, the solid clay, modified with
10 4-amino-1-naphthalenesulfonic acid, was filtrated, and purified until there were no traces of chlorine ions present anymore. The material obtained was subsequently freeze-dried.

 The thus modified clay was used in an organic/inorganic hybrid composition. This composition contained 50 mol% of
15 3-glycidoxypropyltrimethoxysilane (Aldrich), 30 mol% of methyltrimethoxysilane (Aldrich) and 20 mol% of aluminum-tri(sec)butoxide (Aldrich). This hybrid composition was prepared by mixing of the constituents and hydrolysis utilizing 1 mole equivalent of water, based on the amount of alkoxides.

20 35 Grams of the hybrid composition (solids content 40 % by weight) were mixed with 1.09 grams of the modified clay. This amount is equivalent to 5 % by weight of clay, based on solids weight. A coating was applied and it was cured for 3 hours at 150°C. It was found that the layer thickness could simply be varied between 1 and 10 µm.

25 This is not possible with formulations not containing modified clay, because they often exhibit cracks.

CLAIMS

1. A method for preparing a composition for a coating, wherein a layered, inorganic filler is subjected to an ion exchange with a modifier, which modifier comprises at least two ionic groups, which groups are separated from each other by at least four atoms, and wherein the modified
5 filler, together with a polymer, is dispersed in a diluent.
2. A method according to claim 1, wherein the layered, inorganic filler is a natural or synthetic clay with a cation exchange capacity of 30-200 milliequivalents per 100 grams.
3. A method according to claim 2, wherein the modifier comprises at
10 least one cationic group.
4. A method according to claim 3, wherein the cationic group is an ammonium, phosphonium or sulfonium group.
5. A method according to claim 1, wherein the layered inorganic filler is a natural or synthetic layered double hydroxide.
- 15 6. A method according to claim 5, wherein the layered double hydroxide satisfies the formula (I):

$$[M_{(1-x)}^{2+} M_x^{3+} (OH)_2] [A_{x/y}^{y-} \cdot n H_2O] \quad (I),$$
 wherein M^{2+} is a bivalent cation, M^{3+} is a trivalent cation, x is a number between 0.15 and 0.5, y is 1 or 2, n is a number from 1 to 10, and A is an
20 anion selected from the group consisting of Cl^- , Br^- , NO_3^- , SO_4^{2-} and CO_3^{2-} .
7. A method according to claim 5 or 6, wherein the modifier comprises at least one anionic group.
8. A method according to claim 7, wherein the anionic group is a carbonate, sulfonate, or phosphonate group.
- 25 9. A method according to any one of the preceding claims, wherein the modifier comprises an aromatic group.
10. A method according to any one of the preceding claims, wherein the modifier is an organic dye.

11. A method according to any one of the preceding claims, wherein the diluent is polar.
12. A method according to any one of the preceding claims, wherein the polymer is selected from the group of polyurethanes; polyacrylates; polymethacrylates; polyesters; polyethers; polyolefins; polystyrene; polyvinyl chloride; alkyds; nitrocellulose; epoxides; phenol resins; amino resins; silicones; polysiloxanes, organic-inorganic hybrid materials; and combinations thereof
13. A method according to any one of the preceding claims, wherein further an initiator is dispersed in the diluent.
14. A composition for coating obtainable according to any one of the preceding claims.
15. A composition for coating comprising a polymer and a modified layered inorganic filler dispersed in a diluent, wherein the filler is modified by ion exchange with a modifier which comprises at least two ionic groups, which groups are separated from each other by at least four atoms.
16. Use of a composition according to claim 14 or 15 for forming a coating.
17. A coating formed upon curing of an applied composition according to claim 14 or 15.
18. A layered inorganic filler modified by ion exchange with a modifier which comprises at least two ionic groups, which groups are separated from each other by at least four atoms.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL 00/00479

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C01B33/44 C08K9/04 C08J3/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C01B C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 791 556 A (NIPPON PAINT CO LTD) 27 August 1997 (1997-08-27) cited in the application claims 1-11 ---	1-18
A	EP 0 681 990 A (RHEOX INT) 15 November 1995 (1995-11-15) claims 1-18 ---	1-18
A	DATABASE WPI Section Ch, Week 199538 Derwent Publications Ltd., London, GB; Class A25, AN 1995-290037 XP002141992 & JP 07 187657 A (AGENCY OF IND SCI & TECHNOLOGY), 25 July 1995 (1995-07-25) abstract --- -/-	1-18

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

21 November 2000

Date of mailing of the international search report

29/11/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ketterer, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL 00/00479

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	EP 0 952 187 A (RHEOX INC) 27 October 1999 (1999-10-27) abstract	1-18
P, A	<div style="text-align: center;">---</div> WO 00 09599 A (ENGELHARDT THOMAS ;COUTELLE HELMUT (DE); SCHALL NORBERT (DE); SELL) 24 February 2000 (2000-02-24) abstract <div style="text-align: center;">-----</div>	1,5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 00/00479

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0791556	A	27-08-1997	JP 9227118 A	02-09-1997
			CA 2198051 A	22-08-1997
			US 5786417 A	28-07-1998
EP 0681990	A	15-11-1995	US 5429999 A	04-07-1995
			CA 2148396 A	12-11-1995
			DE 69513439 D	30-12-1999
			DE 69513439 T	31-05-2000
JP 7187657	A	25-07-1995	JP 2514780 B	10-07-1996
EP 0952187	A	27-10-1999	JP 2000026655 A	25-01-2000
WO 0009599	A	24-02-2000	DE 19836580 A	17-02-2000